

TECHNICAL DATA SHEET
L20-31203 327/00057

Product	LDPE recycle black
Density (g/cm³)	0.92 ± 5% g/cm ³
Thicknesses (μm)	50 μm (±15%)
Width (mm)	420x2+165x4 mm (-0,+40mm)
Length	1200 mm (-0,+20mm)

Mechanical properties:

	Norm	Method
Tear Strength σ_R	MD >14 Mpa	ISO 527-3
	TD >14 Mpa	500 mm/min
Elongation at break, ϵ_R	MD >350 %	ISO 527-3
	TD >450 %	500 mm/min

The articles should be stored in sheltered storage facilities away from direct sunlight at the temperature of 15-30° C , relative humidity of 40-65%, at least 1 meter away from heat sources. Before use, the film should be kept at the operating temperature for at least 24 hours.

The Declaration of Conformity is valid for one year after the date of its signature.

Position: D.Vaškelis, Technologist

